




NOTES :

1. TEMPORARY PATCH:
 - a. HL-8 ASPHALT IN TWO LIFTS TO TOP COURSE ELEVATION COLD MIX ASPHALT WILL BE PERMITTED ONLY IF HL-8 UNAVAILABLE DUE TO WEATHER.
 - b. TO REMAIN IN PLACE FOR ONE FREEZE/THAW CYCLE.
 - c. TO BE GROUND OUT AND REPLACED WITH HL-3.
2. PERMANENT PATCH:
 - a. 35mm HL-3 & 50mm HL-8 OR REPLACE IN KIND.
 - b. TO BE KEYED IN.
3. SAND TO BE COMPACTED IN 150mm LIFTS TO 95% PROCTOR DENSITY.
4. GRANULAR TO BE COMPACTED TO 100% PROCTOR DENSITY.
5. ASPHALT TO BE COMPACTED TO 97% PROCTOR DENSITY.

FROST TAPER TREATMENT AND
RESTORATION REQUIREMENTS FOR
OPEN CUT ROAD CROSSINGS

All dimensions are in millimetres unless otherwise noted.

City of Pickering		Engineering Services Department	
DRAWN P. NEUMAN	FROST TAPER TREATMENT FOR PAVED ROADS	REVISION NO.	2
APPROVED S. A. VOKES		DATE	NOVEMBER 2019
DATE JANUARY 1993		P-430	